



BDE™ 1001

DESCRIPTION

BDE 1001™ is a VOC free, phosphate free micro etching masonry cleanser. **BDE 1001™** prepares all masonry surfaces to receive specialty coating applications. **BDE 1001™** is seal and eco logo approved. **BDE 1001™** concrete cleanser removes stubborn efflorescence.

TECHNICAL AND PRODUCT DATA

- Appearance: Clear liquid
- Freezing point: -5°F (-20°C)
- Specific gravity: 0.98-1.0
- Solubility: 100% in water
- Boiling: 212°F (100°C)
- pH: 1

APPLICATION INSTRUCTIONS

Pre-wet the surface and apply **BDE 1001™** at the rate of 250-300 square feet per gallon. Let stand on the surface for 10 minutes. Flush through entire area with water and inspect surface to ensure all stains, efflorescence, etc. are removed. If recoating is necessary, repeat the process. To test for coating application drop water on the dry surface to make sure it absorbs into the surface immediately.

COVERAGE

250-300 square feet per gallon. Porosity and conditions of surface will vary for each slab, a small test is recommended to achieve desired results prior to ordering.

SPECIAL HANDLING

- D.O.T. regulation: non regulated ground shipment.
- T.D.G. corrosive liquids class 8. See SDS for more information.
- Do not allow to freeze.
- If cleaning near grass or shrubs, water well before starting.

MAJOR ADVANTAGES

- Low pH organic salt
- Non corrosive to skin
- Non fuming
- Water soluble
- Phosphate free
- VOC free
- Stronger than hydrochloric acid
- Removes efflorescence
- Will not deteriorate masonry surfaces
- Fast and easy to use
- Cost effective
- More effective than acids such as; phosphate, citric, glycolic, sulphamic, oxalic.



SPECIALTY
PRODUCTS
GROUP

BDE™ 1001

SAFETY

Please refer to SDS at spgGoGreen.com or contact SPG.

WARRANTY DISCLAIMER

The information herein is to assist customers in determining whether our products are suitable for their application. Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to the contents and suitability. We warrant that our products will meet our written specifications. Nothing herein shall constitute a warranty expressed or implied, including any warranty of merchantability or fitness, nor is protection from any loss or patent to be inferred. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.